



FirstCut HD						
FirstCut HD 80	80%	80%	99%	4.7%	3.8%	55%
FirstCut HD 34	34%	92%	99%	5.0%	5.0%	82%
	Visible Light	IR	UV	Interior	Exterior	Solar Energy
	Transmitted	Rejection	Rejection	Reflection	Reflection	Rejection

FirstCut												
FC 5 PS SR	41%	7%	52%	7%	5%	1.06	1.12	99%	0.64	0.56	92%	45%
FC 20 PS SR	45%	6%	49%	17%	5%	1.10	1.14	99%	0.67	0.58	81%	42%
FC 35 PS SR	48%	6%	46%	35%	6%	1.10	1.14	99%	0.69	0.60	60%	40%
FC 42 PS SR	66%	7%	27%	41%	6%	1.04	1.05	99%	0.85	0.73	54%	27%
FC 55 PS SR	63%	7%	30%	54%	7%	1.11	1.14	99%	0.82	0.71	39%	29%
FC 56 PS SR	69%	8%	24%	53%	7%	1.04	1.05	99%	0.87	0.76	41%	24%
	Total Solar Energy			Visible Light		"U" Factor						
	Transmitted	Reflected	Absorbed	Transmitted	Reflected	Median	Design	UV Rejection	Shading Coefficient	Solar Heat Gain Coefficient	Glare Reduction	Total Solar Energy Rejected

FirstCut Standard												
FCS 5 - PS SR	49%	6%	45%	6%	5%	1.04	1.05	99%	0.73	0.64	93%	36%
FCS 20 - PS SR	57%	6%	37%	23%	5%	1.04	1.05	99%	0.78	0.68	75%	32%
FCS 32 - PS SR	59%	7%	34%	31%	5%	1.03	1.04	99%	0.8	0.7	66%	30%
FCS 38 - PS SR	64%	6%	30%	42%	5%	1.04	1.05	99%	0.84	0.73	53%	27%
FCS 50 - PS SR	66%	7%	27%	50%	5%	1.03	1.04	99%	0.85	0.74	45%	26%
	Total Solar Energy			Visible Light		"U" Factor						
	Transmitted	Reflected	Absorbed	Transmitted	Reflected	Median	Design	UV Rejection	Shading Coefficient	Solar Heat Gain Coefficient	Glare Reduction	Total Solar Energy Rejected

Wincos - Premium Series IR Film													
Wincos 20	15%	7%	77%	21%	8%	1.10	1.14	99%	0.43	0.37	76%	62%	90%
Wincos 30	20%	7%	73%	31%	8%	1.09	1.13	99%	0.47	0.41	65%	59%	90%
Wincos 45	28%	5%	66%	45%	6%	1.09	1.13	99%	0.54	0.47	49%	53%	88%
Wincos 60	35%	8%	58%	60%	9%	1.09	1.13	99%	0.59	0.51	32%	49%	90%
Wincos 70	35%	9%	57%	63%	10%	1.09	1.13	99%	0.58	0.50	28%	49%	92%
	Transmitted	Reflected	Absorbed	Transmitted	Reflected	Median	Design	UV Rejection	Shading Coefficient	Solar Heat Gain Coefficient	Glare Reduction	Total Solar Energy Rejected	Infrared Rejection